

---

**Question 44: What are refiner's practices or procedures to remove catalyst from a reactor when the catalyst will not free flow dump? What is the industry's experience with hydro drilling for removal of non-free-flow catalyst from fixed-bed units?**

**SHARPE** (Flint Hills Resources, LP)

We typically vacuum out catalyst in an inert atmosphere if the reactors do not free-flow dump. We also wet-dump some of our reactors, which involves vacuuming out the catalyst after removing the water. For people who are involved in turnaround planning, unloading rates for free-flowing catalyst are approximately 200 cubic feet of catalyst per hour. Vacuuming out catalyst removes about 140 cubic feet of catalyst per hour, but it does not slow the catalyst. It removes about 100 cubic feet per hour.

# Catalyst Unloading

- We typically vacuum catalyst out of the reactors in an inert atmosphere if they don't free-flow dump.
- We also wet dump some of our reactors, which involves vacuuming out the catalyst after removing the water.
- Unloading rates for free-flowing catalyst are approximately 200 cu. Ft. of catalyst per hour, vacuuming out catalyst removes approximately 140 cu. Ft. of catalyst per hour, and vacuuming out dense loaded catalyst removes approximately 100 cu. Ft. of catalyst per hour.

---

It is pretty difficult to unload free flow dumping through a bottom nozzle. The support material will fall out first, leaving a cavity which can cause an engulfment hazard; so that is not recommended. Another method for removing non-flowing catalyst is using the hydroblast wand through the bottom dump level to wash catalyst out from the bottom of the reactor. This would be a form of hydro drilling. The other method some people have used is blasting catalyst out of the reactors for bottom-dumping using explosive charges. Charges are inserted in the catalyst bed and set off; catalyst then free-flows out of the bottom-dump nozzles. The Dwayne Hoakum Company is still around, as well as other companies. This company used to do this on our Cumene reactors, and they also perform a service on hydrotreater reactors for other companies.

# Catalyst Unloading

- Dense loaded catalyst is very difficult to free flow dump through a bottom nozzle- the support material frequently falls out and leaves a cavity causing an engulfment hazard.
- 2 other methods for removing non-flowing catalyst are :
  - 1. Using a hydroblast wand through the bottom dump nozzle to wash out catalyst from the bottom of the reactor up (this would be a form of hydrodrilling), and
  - 2. Blasting catalyst out of the reactors for bottom dumping- a charge is inserted in the catalyst bed from the bottom and set off- the catalyst free-flows out the bottom. Dwayne Hoakum Co. used to do this on our Cumene reactors, and performs this service on hydrotreater reactors for other companies.

---

**VICHAILAK** (Marathon Petroleum Corporation)

At Marathon, we prefer catalyst removal under an inert atmosphere. As long as there is catalyst in the reactor, the atmosphere will stay inert. We prefer to select the method for removing catalyst before we shut down. If that reactor has a history of not being able to free-flow or do a gravity dump, then we plan for unloading with vacuum beforehand. If significant clumping is expected, I have seen catalyst handlers go down with a jackhammer to get the catalyst out one layer at a time. If we decide to do gravity dump and catalyst stops free-flowing, we will not allow anyone to go into the reactor, period. So in that situation, all operations will be managed from outside. Lately you have heard about CO<sub>2</sub> (carbon dioxide) blasting having good promise, but we have not used it yet. We have never done hydrodrillings or experienced any wet loading so far.

Q-44

## MPC Preferred Practices on Reactor Unloading



- *Complete catalyst removal under inert atmosphere*
- *Preferred method of Unloading must be selected before unit shutdown*
- *If significant clumping is expected, vacuum unloading allows safe work zone to “jackhammer”*
- *If catalyst stops free-flowing, manage from outside*
- *CO<sub>2</sub> blasting appears to have high promise but we’ve not used it yet*
- *No experience with Wet Unloading*

---

Print as PDF:

Tags

[Catalysts](#)

[Operations](#)

[Reactor Vessel](#)

Year

2013